



Designation: F30 – 96 (Reapproved 2017)

Standard Specification for Iron-Nickel Sealing Alloys¹

This standard is issued under the fixed designation F30; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers iron-nickel alloys that are intended primarily for sealing to glass in electronic applications.

NOTE 1—Some of these alloys may be used for sealing to ceramics, but this specification in its present form is not intended to cover material for metal-to-ceramic seals.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* The hazard statement pertains only to the test method sections, Sections 10 and 12.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E18 Test Methods for Rockwell Hardness of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E112 Test Methods for Determining Average Grain Size

E228 Test Method for Linear Thermal Expansion of Solid Materials With a Push-Rod Dilatometer

¹ This specification is under the jurisdiction of ASTM Committee F01 on Electronics and is the direct responsibility of Subcommittee F01.03 on Metallic Materials, Wire Bonding, and Flip Chip.

Current edition approved June 1, 2017. Published June 2017. Originally approved in 1977. Last previous edition approved in 2012 as F30–96 (2012). DOI: 10.1520/F0030-96R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

F14 Practice for Making and Testing Reference Glass-Metal Bead-Seal

F140 Practice for Making Reference Glass-Metal Butt Seals and Testing for Expansion Characteristics by Polarimetric Methods

F144 Practice for Making Reference Glass-Metal Sandwich Seal and Testing for Expansion Characteristics by Polarimetric Methods

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Size,

3.1.2 Temper (Section 6),

3.1.3 Surface finish (Section 8),

3.1.4 Marking and packaging (Section 16), and

3.1.5 Certification if required.

4. Chemical Composition

4.1 The material shall conform to the requirements as to chemical composition prescribed in Table 1.

5. Surface Lubricants

5.1 All lubricants used in processing shall be thoroughly removed. Protective coatings present on the material as shipped shall be readily removable by any of the common organic degreasing solvents.

6. Temper

6.1 The desired temper of the material shall be specified on the purchase order. Unless otherwise specified, wire, rod, bar, and tubing shall be given a final bright anneal by the manufacturer. Strip and sheet shall be annealed properly to develop deep drawing properties. For deep drawing the hardness shall not exceed Rockwell B82 for material 0.100 in. (2.54 mm) and less in thickness, and B85 for material over 0.100 in. thick when determined in accordance with Test Methods E18.

7. Grain Size

7.1 Strip and sheet for deep drawing applications shall have an average grain size not larger than ASTM No. 5 (Note 2) and no more than 10 % of the grains shall be larger than No. 5 when measured in accordance with Test Methods E112. For

TABLE 1 Chemical Requirements

	Composition, %				
	42 Alloy UNS K94100	46 Alloy UNS K94600	48 Alloy UNS K94800	51 Alloy	52 Alloy UNS N14052
Nickel, ^A nominal	41	46	48	51.5	50.5
Manganese, max	0.80	0.80	0.80	0.60	0.60
Silicon, max	0.30	0.30	0.30	0.30	0.30
Carbon, max	0.05	0.05	0.05	0.05	0.05
Chromium, max	0.25	0.25	0.25	0.25	0.25
Cobalt, max	^B	^B	^B	^B	^B
Phosphorus, max	0.025	0.025	0.025	0.0250	0.025
Sulfur, max	0.025	0.025	0.025	0.0250	0.025
Aluminum, max	0.10	0.10	0.10	0.100	0.10
Iron	remainder	remainder	remainder	remainder	remainder

^A The nickel contents listed are nominal. The nickel contents of the alloys shall be adjusted by the manufacturer so that the alloys meet the requirements for thermal expansion. The 52 Alloy is specifically intended to match lead (Pb) sealing glasses.
^B Cobalt is present as an incidental element and shall be reported separately.

materials less than 0.005 in. (0.13 mm) in thickness the grain size shall be such that there are no less than 4 grains across the thickness.

NOTE 2—This corresponds to a grain size of 0.065 mm or 16 grains/in. of image of 100×

8. Surface Finish

8.1 The standard surface finishes available shall be those resulting from the following operations:

- 8.1.1 Hot-rolling,
- 8.1.2 Forging,
- 8.1.3 Centerless grinding (rod),
- 8.1.4 Belt polishing,
- 8.1.5 Cold rolling, and drawing, and
- 8.1.6 Wire drawing.

9. Thermal Expansion Characteristics

9.1 The average linear coefficients of thermal expansion shall be within the limits specified in **Table 2**.

TABLE 2 Thermal Expansion Requirements^A

UNS Number	Alloy No.	Temperature Range, °C	Average Linear Coefficient of Thermal Expansion, $\mu\text{m/m}\cdot^\circ\text{C}$
K94100	42	30 to 300 30 to 450	4.0 to 4.7 6.7 to 7.4
K94600	46	30 to 350 30 to 500	7.1 to 7.8 8.2 to 8.9
K94800	48	30 to 400 30 to 550	8.2 to 9.2 9.6 to 10.3
...	51	30 to 450 30 to 550	9.9 to 10.5 10.0 to 10.7
N14052	52	30 to 450 30 to 550	9.7 to 10.2 10.0 to 10.5

^A Typical expansion data up to 1000°C are given in the Appendix.

10. Test for Thermal Expansion

10.1 Determine the thermal expansion characteristics with a precision dilatometer after heating the specimen as follows:

10.1.1 Heat the specimen in a hydrogen atmosphere for 1 h at 900°C and then cool it from 900 to 200°C at a rate not exceeding 5°C/min.

10.1.2 The thermal expansion properties are determined in accordance with Test Method **E228**.

10.2 The thermal expansion match between the alloy and a glass may be evaluated by testing the assembly in accordance with Practices **F14**, **F140**, or **F144**.

11. Dimensions and Permissible Variations

11.1 *Cold-Rolled Strip*—Cold-rolled strip shall conform to the permissible variations in dimensions prescribed in **Table 3**, **Table 4**, and **Table 5**.

11.2 *Round Wire and Rod*—Wire and rod shall conform to the permissible variations in dimension prescribed in **Table 6**.

11.3 *Cold-Drawn Tubing*—Cold-drawn tubing, available either as seamless or welded, shall conform to the permissible variations prescribed in **Table 7**.

12. Rounding Results

12.1 Observed or calculated values obtained from analysis, measurements, or tests shall be rounded in accordance with Practice **E29**, to the nearest unit in the last right place of figures used in expressing the specified limit.

13. General Requirements

13.1 The material shall be commercially smooth, uniform in cross section, in composition, and in temper; it shall be free from scale, corrosion, porosity, cracks, seams, scratches, slivers, and other defects as best commercial practice will permit.

14. Packaging and Package Marking

14.1 Packaging shall be subject to agreement between the purchaser and the seller.

14.2 The material as furnished under this specification shall be identified by the name or symbol of the manufacturer and by melt number. The lot size for determining compliance with the requirements of this specification shall be one heat.

15. Investigation of Claims

15.1 Where any material fails to meet the requirements of this specification, the material so designated shall be handled in accordance with the agreement mutually agreed upon by the purchaser and the seller.

16. Keywords

16.1 glass-to-metal sealing applications; iron-nickel alloys; UNS K94600; UNS K94800; UNS N14052; vacuum electronics

TABLE 3 Permissible Variations in Thickness of Cold-Rolled Strip

NOTE 1—Measurements shall be made at least $\frac{3}{8}$ in. (9.5 mm) from the edge of strip that is over 1 in. (25.4 mm) wide.

Specified Thickness, in. (mm)	Permissible Variations in Thickness for Width Given, plus or minus, in. (mm)							
	Under 3 (76)		Over 3 to 6 (76 to 152)		Over 6 to 12 (152 to 305)		Over 12 to 16 (305 to 406)	
0.160 to 0.100 (4.06 to 2.54), incl	0.002	(0.051)	0.003	(0.076)	0.004	(0.102)	0.004	(0.102)
0.099 to 0.069 (2.51 to 1.75), incl	0.002	(0.051)	0.003	(0.076)	0.003	(0.076)	0.004	(0.102)
0.068 to 0.050 (1.73 to 1.27), incl	0.002	(0.051)	0.003	(0.076)	0.003	(0.076)	0.003	(0.076)
0.049 to 0.035 (1.24 to 0.89), incl	0.002	(0.051)	0.0025	(0.064)	0.003	(0.076)	0.003	(0.076)
0.034 to 0.029 (0.86 to 0.74), incl	0.0015	(0.038)	0.002	(0.051)	0.0025	(0.064)	0.0025	(0.064)
0.028 to 0.026 (0.71 to 0.66), incl	0.0015	(0.038)	0.0015	(0.038)	0.002	(0.051)	0.002	(0.051)
0.025 to 0.020 (0.64 to 0.51), incl	0.001	(0.025)	0.0015	(0.038)	0.002	(0.051)	0.002	(0.051)
0.019 to 0.017 (0.48 to 0.43), incl	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)	0.002	(0.051)
0.016 to 0.012 (0.41 to 0.31), incl	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)	0.0015	(0.038)
0.011 to 0.0101 (0.28 to 0.26), incl	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)
0.010 to 0.0091 (0.25 to 0.23), incl	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)
0.009 to 0.006 (0.23 to 0.15), incl	0.00075	(0.019)	0.00075	(0.019)	...		...	
Under 0.006 (0.15)	0.0005	(0.013)	0.0005	(0.013)	...		...	

TABLE 4 Permissible Variations in Thickness Across Width of Cold-Rolled Strip

Specified Thickness, in. (mm)	Maximum Variation in Thickness Across Width of Strip (Within Limits Specified in Table 3 for Edge Measurements) for Widths and Thicknesses Given, in. (mm)			
	5 (127) and under		Over 5 to 12 (127 to 305)	Over 12 to 24 (305 to 610), incl
0.005 to 0.010 (0.13 to 0.25), incl	0.00075 (0.019)		0.001 (0.025)	0.0015 (0.038)
Over 0.010 to 0.025 (0.25 to 0.64), incl	0.001 (0.025)		0.0015 (0.038)	0.002 (0.051)
Over 0.025 to 0.065 (0.64 to 1.65), incl	0.0015 (0.038)		0.002 (0.051)	0.0025 (0.064)
Over 0.065 to $\frac{3}{16}$ (1.65 to 4.8), excl	0.002 (0.051)		0.0025 (0.064)	0.003 (0.076)

TABLE 5 Permissible Variations in Width of Coil-Rolled Strip Supplied in Coils

Specified Thickness, in. (mm)	Permissible Variations in Width for Widths Given, plus or minus, in. (mm)				
	Under $\frac{1}{2}$ to $\frac{3}{16}$ (12.7 to 4.8)	$\frac{1}{2}$ to 6 (12.7 to 152)	Over 6 to 9 (152 to 229)	Over 9 to 12 (229 to 305)	Over 12 to 20 (305 to 508)
0.187 to 0.161 (4.75 to 4.09)	...	0.016 (0.41)	0.020 (0.51)	0.020 (0.51)	0.031 (0.79)
0.160 to 0.100 (4.06 to 2.54)	0.010 (0.25)	0.010 (0.25)	0.016 (0.41)	0.016 (0.41)	0.020 (0.51)
0.099 to 0.069 (2.51 to 1.75)	0.008 (0.20)	0.008 (0.20)	0.010 (0.25)	0.010 (0.25)	0.016 (0.41)
0.068 (1.73) and under	0.005 (0.13)	0.005 (0.13)	0.005 (0.13)	0.010 (0.25)	0.016 (0.41)

TABLE 6 Permissible Variations in Diameter of Wire and Rod

Specified Diameter, in. (mm)			Permissible Variations in Diameter, plus or minus, in. (mm)	
Wire (Coiled, Spooled, or Straight Lengths)				
0.002	to 0.0043	(0.051 to 0.109)	0.002	(0.051)
0.0044	to 0.0079	(0.112 to 0.201)	0.00025	(0.006)
0.008	to 0.0149	(0.203 to 0.378)	0.0003	(0.007)
0.015	to 0.0199	(0.381 to 0.505)	0.0004	(0.010)
0.020	to 0.0309	(0.508 to 0.785)	0.0005	(0.013)
0.031	to 0.0409	(0.787 to 1.039)	0.0006	(0.015)
0.041	to 0.0609	(1.041 to 1.547)	0.0007	(0.018)
0.061	to 0.0809	(1.549 to 2.055)	0.0008	(0.020)
0.081	to 0.1259	(2.057 to 3.198)	0.001	(0.025)
0.126	to 0.1569	(3.200 to 3.985)	0.0015	(0.038)
0.157	to 0.250	(3.99 to 6.35)	0.002	(0.051)
Rod, Centerless Ground Finish (Straight Lengths)				
0.030	to 0.0549	(0.762 to 1.394)	0.0005	(0.013)
0.055	to 0.1249	(1.397 to 3.172)	0.001	(0.025)
0.125	to 0.499	(3.175 to 12.67)	0.0015	(0.038)
0.500	to 0.999	(12.70 to 25.38)	0.002	(0.051)
1.000	to 1.625	(25.40 to 41.27)	0.0025	(0.064)
1.626	to 1.749	(41.30 to 44.43)	0.003	(0.076)
1.750	to 1.999	(44.45 to 50.78)	0.004	(0.102)
2.000	to 4.000	(50.80 to 101.60)	0.005	(0.13)

TABLE 7 Permissible Variations in Dimensions of Standard Tubing ^A

Specified Outside Diameter, in. (mm)	Outside Diameter, in. (mm)	Inside Diameter, in. (mm)	Wall Thickness, plus or minus, %
Under 3/32 (2.4)	+ 0.002 (0.051) –0.000	+ 0.000 –0.002 (0.051)	10
3/32 to 3/16 (2.4 to 4.8), excl	+ 0.003 (0.076) –0.000	+ 0.000 –0.003 (0.076)	10
3/16 to 1/2 (4.8 to 12.7), excl	+ 0.004 (0.102) –0.000	+ 0.000 –0.004 (0.102)	10
1/2 to 1 1/2 (12.7 to 38.1), excl	+ 0.005 (0.127) –0.000	+ 0.000 –0.005 (0.127)	10

APPENDIX

(Nonmandatory Information)

X1. THERMAL EXPANSION DATA

X1.1 Typical thermal expansion data for the alloys covered by this specification are given in **Table X1.1** for information only.



TABLE X1.1 Typical Results of Thermal Expansion Tests

Temperature Range, °C	Average Linear Coefficient of Thermal Expansion, $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$				
	42 Alloy UNS K94100	46 Alloy UNS K94600	48 Alloy UNS K94800	51 Alloy	52 Alloy UNS N14052
30 to 300	4.4	7.5	8.8	10.2	10.1
30 to 400	6.0	7.5	8.7	10.2	9.9
30 to 500	7.9	8.5	9.4	10.1	9.9
30 to 600	9.6	9.8	10.4	11.0	10.8
30 to 700	10.5	10.7	11.3	11.9	11.7
30 to 800	11.4	11.6	12.1	12.7	12.5
30 to 900	12.3	12.5	13.0	13.5	13.3
30 to 1000	13.2	13.4	13.9	14.4	14.2

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>